

Industrial DTM Acrylic Primer Interior / Exterior

Matte • 5350

Product Description

Aquatra Industrial Universal DTM Acrylic Primer is a specially formulated acrylic, rust inhibitive, cross-linking primer/sealer. Is designed for use on properly prepared interior and exterior surfaces in light to moderate industrial, maintenance, or new construction climates. Its special formulation offers ease of application, excellent coverage, superior adhesion, moisture and corrosion resistance and convenience. It dries fast, provides excellent durability, resists flash rusting, and is an excellent base coat for both water-based and alkyd/oil-based finish coatings.

<p>Recommended Substrates</p> <ul style="list-style-type: none"> Structural steel, iron & ferrous metals Aluminum and non-ferrous metals Galvanized metals Non-staining wood & fiberglass Rails, piping, tools, tanks, etc. <p>Product Features</p> <ul style="list-style-type: none"> 100% acrylic formula Rust inhibitive & corrosion resistant Excellent coverage and adhesion Early moisture & blister resistant Self cross-linking Soap and water clean up <p>Product Limitations</p> <p>This product is for use on properly prepared above grade horizontal and vertical substrates. Do not apply to horizontal surfaces or areas that come in constant contact with moisture or standing water.</p>	<p>Available bases 5350: WB DB* AB* * SPECIAL ORDER ONLY</p> <p>Application: Brush, roller, airless or conventional spray</p> <p>Dry time @ 50% RH*: 30 - 60 Min to touch 2 - 3 HRS to recoat</p> <p>*dry times listed may vary according to the relative humidity, temperature, film build, color and air movement of the application environment</p> <p>Flash Point: Nonflammable >200°F Clean Up: Warm soapy water</p> <p>Compliance</p> <p>These products are VOC compliant based on limits provided by CARB, EPA, MPI GPS-1, LEEDv4, OTC and SCAQMD.</p>	<p>Product Data</p> <p>Product Type: Waterborne Acrylic</p> <p>Gloss @60°: 5350 5 - 15</p> <p>Wt Solids ±2%: 61% Vol Solids ±2%: 46%</p> <p>Wet Film Mils: 4.0 - 5.3 Dry Film Mils: 1.8 - 2.4 Coverage / Gal * 300 - 400</p> <p>* coverage and wet and dry millage will vary by substrate type and porosity. VOC gms p/L**: <150 ** less exempt solvents. Viscosity KU ±5: 95</p>
--	--	---

Surface Preparation

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

General Surface Preparation: The performance of this product is dependent on the integrity and soundness of the substrate. All surfaces should be clean and free of any dirt, rust, grease, mill oils, mill scale, efflorescence, organic growth, mildew or other contaminants that might adversely affect the adhesion and performance of this product. Any failed or deteriorated caulk or patching compound should be removed and replaced. Unpainted surfaces should be primed in accordance with manufacturer's recommendations. Glossy substrates should be deglossed prior to painting.

Mildew - Surface areas affected by mildew should be treated with a commercial mildew wash and/or removal product carefully following manufacturer's application and safety directions. Rinse thoroughly with clean water and allow a minimum of 24 hours to dry thoroughly.

Ferrous Metals: Thoroughly clean the entire surface area according to SSPC-SP 1 - Solvent Cleaning specifications. Completely remove any existing paint, as well as any loose rust, mill scale and rust deposits by hand scraping, sanding, and wire brushing according to SSPC-SP 2 - Hand Tool Cleaning specifications, or by power tool cleaning methods, such as electric sanders or grinders according to SSPC-SP 3 - Power Tool Cleaning specifications. Previously painted surfaces, whereby the existing paint show signs of serious deterioration should be completely removed in accordance with SSPC-SP 6 - Commercial Blast Cleaning, or SSPC-SP 10 - Near White Blast Cleaning specifications. Repair/ replace any damaged, delaminated and surface imperfections with the proper patching compounds or building materials, and sand all glossy surfaces to effectively existing sheen.

Fiberglass & Galvanized Metals: solvent clean in accordance with SSPC-SP 1, lightly sand fiberglass and prime with this product.

Application: Stir product thoroughly in a spiral up and down motion before use and during application. Use a quality nylon or polyester brush, a 3/8" to 3/4" nap synthetic roller cover, or airless sprayer with a minimum pressure of 2000 PSI and a .015"-.019" tip. To assure color uniformity intermix multiple containers of same color and apply a small test area to verify color.

Thinning: Stir thoroughly and apply as it comes from the container, thinning is not necessary under normal conditions.

Coverage & Dry Time: Covers approximately 300-400 square feet per gallon, depending on the method of application and the porosity of the surface to be painted. Dries to touch in approximately 30-60 minutes and may be recoated in 2-3 hours when humidity is low. Do not use when air, surface or product temperatures are below 50°F or above 100°F. Cleaning should not occur until 30 days after the initial application.

Clean Up: Minor spills and splatters should be immediately cleaned with soap and water, as well as any painting tools and airless spray equipment. More serious spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

Safety - CAUTIONS: KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY! USE ONLY WITH ADEQUATE VENTILATION! Avoid prolonged contact with skin, and breathing of dust, vapors or spray mists. Avoid contact with eyes and wear eye protection. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Wash skin thoroughly after handling. Close container after each use and store in a secure, shaded and dry location. **First Aid:** Wash skin thoroughly with plenty of warm soap and water. In case of eye contact immediately flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing leave area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed do not induce vomiting and get medical attention immediately.

Storage and Disposal

Product should be kept from freezing temperatures or temperatures above 95°F. Refer to your local city or county government for instructions on disposal options.

Florida Paints believes the technical data represented in this technical bulletin to be current and up to date. However, Florida Paints makes no warranties or guarantees either expressed or implied. Florida Paints claims no responsibility from damages incurred from use by either the purchaser or user of the product.

PDS 5350 2007



Please excuse the small print used on this document but most paint company datasheets are two pages long. By squeezing all this information on one page we are doing our part to save a few trees.

Florida Paints and Coatings, LLC
78 3rd Street | Winter Garden, Florida 34787
407.986.1000 | info@FloridaPaints.com | FloridaPaints.com